

SATRA Technology Centre Ltd Wyndham Way, Telford Way, Kettering, Northamptonshire, NN16 8SD United Kingdom Tel: +44 (0) 1536 410000 Fax +44 (0) 1536 410626

email: <u>info@satra.com</u> www.satra.com



Customer details: Sensorybeanbags

Doonavanig

Minane Bridge

Kinsale County Cork

Eire

P17 EY86

Date of report: 19th April 2017

SATRA reference: CHM0255900/1713/EN

PO 4834

Samples received: 29th March 2017

Date(s) work 11th April 2017

carried out:

Your reference:

For the attention of: Julie Hannon

TECHNICAL REPORT

Subject: BS EN 71-3: 2013 + A1: 2014 migration of certain elements on material

described as 'Dance Lycra' from Sensory Beanbag.

Conditions of Issue:

This report may be forwarded to other parties provided that it is not changed in any way. It must not be published, for example by including it in advertisements, without the prior, written permission of SATRA.

Results given in this report refer only to the samples submitted for analysis and tested by SATRA. Comments are for guidance only.

Tests marked ≠ fall outside the UKAS Accreditation Schedule for SATRA. All interpretations of results of such tests and the comments based upon them are outside the scope of UKAS accreditation and are based on current SATRA knowledge.

A satisfactory test report in no way implies that the product tested is approved by SATRA and no warranty is given as to the performance of the product tested. SATRA shall not be liable for any subsequent loss or damage incurred by the client as a result of information supplied in the report.

The uncertainty of the results (UoM) in this report is based on a standard uncertainty multiplied by a coverage factor k=2, which provides for a confidence level of approximately 95%.

Report signed by: Emma Norris

Position: Chemical Technologist

Department: Chemical & Analytical Technology

(Page 1 of 6)







WORK REQUESTED:

Material described as 'Dance Lycra' from Sensory Beanbag was received on the 29th March 2017 for migration testing in accordance with the requirements for 'Category III' materials as described in BS EN 71-3:2013+A1:2014.

CONCLUSIONS:

When tested in accordance with BS EN 71-3:2013+A1:2014 and SATRA SOP CAT-003, the material described as 'Dance Lycra' from Sensory Beanbag was found to meet the requirements for 'Category III' materials.

Full results are provided in the table below.

TESTING REQUIRED:

• BS EN 71-3:2013+A1:2014. Safety of toys. Migration of certain elements

Sensorybeanbags SATRA Reference: Date:

CHM0255900/1713/EN 19th April 2017 Signed:

(Page 2 of 6)





RESULTS AND REQUIREMENTS:

SATRA SOP CAT-003 – Migration of 'general elements' from toy materials. (In accordance with clause 7.4 & Annex E of BS EN 71-3:2013+A1:2014)

Analysed by Inductively Coupled Plasma with Mass Spectrometry (ICP-MS)

Material reference:	'Dance lycra'		UoM (%)	Category III limits
Procedures**	D4		OOIVI (70)	(mg/kg)
Element	Migration (mg/kg)			(ilig/kg)
Aluminium	< 100	Pass	± 44	70,000
Antimony	< 5	Pass	± 66	560
Arsenic	< 0.5	Pass	± 65	47
Barium	< 10	Pass	± 35	18,750
Boron	< 50	Pass	± 43	15,000
Cadmium	< 0.1	Pass	± 27	17
Chromium*1	< 0.2	Pass	± 18	460 (Cr III) 0.2 (Cr VI)
Cobalt	< 1	Pass	± 35	130
Copper	< 1	Pass	± 34	7,700
Lead	< 0.5	Pass	± 38	160
Manganese	< 10	Pass	± 37	15,000
Mercury	< 0.2	Pass	± 35	94
Nickel	< 1	Pass	± 39	930
Selenium	<1	Pass	± 51	460
Strontium	< 10	Pass	± 44	56,000
Tin	< 1	Pass	± 44	180,000
Organic Tin*2	Pass		N/A	12
Zinc	< 50	Pass	± 43	46,000

^{*1} First action screening method. Where the elemental chromium result (including uncertainty of measurement) is below 0.2 mg/kg, it can be inferred that this meets the requirements for both chromium (III) and chromium (VI).

Sensorybeanbags SATRA Reference:

CHM0255900/1713/EN Date:

19th April 2017

Signed:

(Page 3 of 6)

^{*2} First action screening method. Where the elemental tin result (including uncertainty of measurement) is below 4.92 mg/kg, it can be inferred that this also meets the requirement for organic tin.





APPENDICES:



HOLOGY

Sample described as 'Dance Lycra'

Migration limits as set out in BS EN 71-3:2013+A1:2014

Element	Category I (mg/kg)	Category II (mg/kg)	Category III (mg/kg)
Aluminium	5,625	1,406	70,000
Antimony	45	11.3	560
Arsenic	3.8	0.9	9 47
Barium	1,500	375	18,750
Boron	1,200	300	15,000
Cadmium	1.3	0.3	17
Chromium (III)	37.5	9.4	460
Chromium (VI)	0.02	0.005	0.2
Cobalt	10.5	2.6	130
Copper	622.5	156	7,700
Lead	13.5	3.4	160
Manganese	1,200	300	15,000
Mercury	7.5	1.9	94
Nickel	75	18.8	930
Selenium	37.5	9.4	460
Strontium	4,500	1,125	56,000
Tin	15,000	3,750	180,000
Organic Tin	0.9	0.2	12
Zinc	3,750	938	46,000

Sensorybeanbags

SATRA Reference: Date:

CHM0255900/1713/EN 19th April 2017

(Page 4 of 6)

Signed:





BS EN 71-3:2013+A1:2014 clause H.4-Toy Categories

Category I: Dry brittle, powder like or pliable

Category I includes solid toy material from which powder-like material is released during play. The material can be ingested. Contamination of the hands with powder contributes to enhanced oral exposure. The assumed ingestion is 100mg per day.

Category II: Liquid or sticky

Category II includes fluid or viscous toy material which can be ingested and/or to which dermal exposure occurs during playing. The assumed ingestion is 400mg per day.

Category III: Scraped off

Category III includes solid toy material with or without a coating which can be ingested as a result of biting, tooth scraping, sucking or licking. This category includes those materials which are not covered be category I and II. The assumed ingestion is 8 mg per day.

**Preparation & Migration Procedures

Samples were prepared and tested in accordance with the following clauses of BS EN 71-3:2013+A1:2014:

Preparation procedure

- A 7.3.3.1 Coatings of paint, varnish, lacquer, printing ink, polymer and similar coatings
- B 7.3.3.2 Polymeric materials
- C 7.3.3.3 Paper and paper board
- D 7.3.3.4 Textiles (natural or synthetic)
- E 7.3.3.5 Glass, ceramic and metallic materials
- F 7.3.3.6 Other materials, whether mass coloured or not

Migration procedure

- 1 7.4.3.1 Coatings of paint, varnish, lacquer, printing ink, polymer and similar coatings
- 2 7.4.3.2 Polymeric materials
- 3 7.4.3.3 Paper and paper board
- 4 7.4.3.4 Textiles (natural or synthetic)
- 5 7.4.3.5 Accessible glass, ceramic and metallic materials

NOTE: 'Other materials' are tested using the most appropriate procedure of 2, 3, 4 or 5.

Sensorybeanbags SATRA Reference:

CHM0255900/1713/EN

Date: 19th April 2017

Signed:

(Page 5 of 6)





TERMS AND CONDITIONS OF BUSINESS

GENERAL

Work done or services undertaken are subject to the terms and conditions detailed below and all other conditions, warranties and representations, expressed or implied are hereby excluded.

PRICES

Prices are based on current material and production costs, exchange rates, duty and freight and are subject to change without notice.

3. DELIVERY ESTIMATES

Delivery estimates are made in good faith and date from receipt of a written order and full information to enable us to proceed. While SATRA or its subsidiaries (hereafter referred to as "SATRA") make every effort to fulfil them, such estimates are subject to unforeseen events and if not maintained, cannot give rise to any claim. Offers "ex stock" are subject to prior sale.

4. CANCELLATION AND RETURNS

Cancellation of orders for goods, services, training or consultancy is only acceptable by prior agreement of SATRA and a charge will normally be made.

CLAIMS

Claims for errors, shortages etc should be notified within 10 days of date of receipt. In the event of goods damaged in transit, packing materials should be retained for examination; otherwise no liability can be accepted.

6. PAYMENT TERMS

Payment terms are net 21 days from date of invoice. Failure to comply with the terms of payment may result in delayed delivery of goods and services and a review of the Customer's credit account. Should the customer become subject to an administration order, or becomes bankrupt or goes into liquidation, SATRA has a right to cancel any contract and discontinue any work. SATRA reserves the right to adjust US Dollar and Euro sales price where customer exceeds credit terms and where the exchange rate has moved more than 10% since invoicing.

7. RETENTION OF TITLE

All goods remain the property of SATRA until paid in full. Under no circumstances will a customer's purchase order override SATRA's Retention of Title clause. In the case of software, the ownership of the software remains with SATRA. Payment of invoices in full will entitle the customer to use the software under licence until (a) they cease to be a member of SATRA or (b) they cease trading. In both instances, the licence shall then revert to SATRA.

8. GUARANTEE

All goods manufactured by SATRA are guaranteed both as regards material and workmanship. Any part returned carriage paid, within twelve months from date of supply and found defective, will be repaired or replaced at SATRA's option free of charge. SATRA admits no liability for loss, damage or delay consequent on any defect in any goods supplied by SATRA.

9. TEST REPORTS

Results given in test reports refer only to samples submitted for analysis and tested by SATRA. A satisfactory test report in no way implies that the product tested is approved by SATRA and no warranty is given as to the performance of the product tested. SATRA shall not be liable for any subsequent loss or damage incurred by the Customer as a result of information supplied in a test report.

TEST SAMPLES

Unless otherwise agreed in advance, test samples will be disposed of 6 weeks after the date of the final report. If required, samples can be returned at the Customer's expense.

11. RESPONSIBILITY

Every effort is made to ensure accuracy in description, drawings and other information in correspondence, catalogues, etc but no warranty is given in this respect and SATRA shall not be liable for any error therein. SATRA carries out all tests and/or advises only on the basis that the same are carried out, made or given without any responsibility whether for negligence or otherwise. SATRA and its servants or agents will not be liable for any damage or loss direct or indirect of whatsoever kind, whether or not the same results directly or indirectly from negligence on the part of SATRA or its servants or agents.

12. CONFIDENTIALITY

Unless specifically excluded in the terms of an individual contract between SATRA and its Customer, the following shall apply to all reports, advice, drawings, photographs, specifications or data:

- i. The above shall not be disclosed to third parties or used in litigation without the consent of SATRA.
- ii. Where SATRA has given consent to disclosure, the Customer shall draw the attention of the third party to these terms of business and the basis on which SATRA undertakes test, reporting and advising. The Customer shall indemnify SATRA for any failure to do so.
- iii. The above items are submitted to the Customer as confidential documents. Confidentiality shall continue to apply after completion of the business, but shall cease to apply to information or knowledge which may come into the public domain.

13. CONSTRUCTION AND ARBITRATION

The laws of England shall govern all contracts and the parties submit to exclusive jurisdiction of the courts of England, unless otherwise agreed.

Issue Date: 1st October 2009

Sensorybeanbags

SATRA Reference: CHM0255900/1713/EN

Date: 19th April 2017

Signed:

(Page 6 of 6)